


Standard Colors

Weather XL – Siliconized Modified Polyester (SMP)


SMP



Driftwood
SR:0.55 E:0.86 SRI:64




Sandstone
SR:0.49 E:0.86 SRI:56



Surrey Beige
SR:0.41 E:0.86 SRI:45


MP (Modified Polyester)



Imperial White
SR:0.62 E:0.86 SRI:74

Solid Fluropon® PVDF Colors – Kynar 500® / Hylar 5000


Category 1




Regal White
SR:0.70 E:0.86 SRI:85



Ascot White
SR:0.69 E:0.85 SRI:83



Bone White
SR:0.69 E:0.84 SRI:83



Driftwood
SR:0.45 E:0.86 SRI:50



Sandstone
SR:0.61 E:0.85 SRI:72




Surrey Beige
SR:0.48 E:0.86 SRI:54

Category 2



Dove Gray
SR:0.47 E:0.86 SRI:53



Zinc Gray
SR:0.35 E:0.86 SRI:37



Rawhide
SR:0.55 E:0.85 SRI:64



Parchment
SR:0.53 E:0.85 SRI:61



Rock Tan
SR:0.62 E:0.86 SRI:74



Taupestone
SR:0.27 E:0.86 SRI:26



Spartan Bronze
SR:0.31 E:0.85 SRI:31




Redwood
SR:0.38 E:0.86 SRI:41



Slate Blue
SR:0.28 E:0.85 SRI:27

Category 3




Colonial Red
SR:0.32 E:0.86 SRI:33



Evergreen
SR:0.26 E:0.85 SRI:24



Regal Blue
SR:0.26 E:0.85 SRI:24




Tahoe Blue
SR:0.26 E:0.85 SRI:24

Premium Colors


Mica Fluropon Classic® II PVDF Colors



Silversmith
SR:0.53 E:0.79 SRI:59




Zinc
SR:0.55 E:0.79 SRI:62



Champagne Pearl
SR:0.48 E:0.81 SRI:53



Champagne Bronze
SR:0.44 E:0.78 SRI:46



Weathered Zinc
SR:0.33 E:0.84 SRI:33




Copper Penny
SR:0.48 E:0.84 SRI:54

Mica Fluropon Classic® PVDF Colors



Bright Silver
SR:0.57 E:0.81 SRI:65



Rosalind Rose
SR:0.34 E:0.88 SRI:36



Champagne Gold
SR:0.51 E:0.85 SRI:58



Pewter
SR:0.31 E:0.86 SRI:31



Medium Bronze
SR:0.19 E:0.85 SRI:15



Dark Bronze
SR:0.12 E:0.83 SRI:5